

# CHEMRAZ® 605

#### **SEALING SOLUTIONS**

Chemraz® 605 is ideally suited for challenging fluid handling applications. A high-temperature compound with superior compression set resistance, physical properties and excellent chemical resistance, it excels in demanding static and semi-dynamic applications. Chemraz 605 exhibits unparalleled performance with hot amines, steam and water and functions well in temperatures ranging from 0°F to 500°F (-18°C to 260°C).

Available in O-rings, gaskets and many other custom shapes, Chemraz 605 possesses a broad chemical resistance range. The 605 compound is suitable for use in a wide variety of media including acids, caustics, aldehydes, esters, ethers, aromatics, hot water, steam, amines, methanol, ketones, TBA and MTBE.

#### **FEATURES & BENEFITS**

- High-temperature capability
- Excellent compression set resistance
- Broad chemical compatibility for use with a wide range of harsh solutions
- Excellent in amines, hot water and steam
- · NAMSA USP Class VI Certified

### **AVAILABILITY**

- · Mechanical seals
- Mixers
- Medical devices
- Bearing isolators
- Pump housings
- Compressors
- Diagnostic equipment
- Controls/instrumentation

Reactors

- Valves
- Sampling/metering equipment
- · Sprayers/dispensers

## Contact Us

 Greene, Tweed
 Tel: +1.281.821.2094

 Fluid Handling
 Tel: +1.800.820.9005

 Houston, TX, USA
 Fax: +1.281.821.2696



TYPICAL PROPERTIES* Physical Properties	ASTM Method	Typical Value
Specific Gravity	D297	1.97
Hardness, Shore A, Points	D2240	80
Elongation @ Break, %	D1414	130
Tensile Modulus, psi (MPa)		
Modulus @ 50% Elongation	D1414	420 (2.9)
Modulus @ 100% Elongation	D1414	1310 (9.0)
Tensile Strength @ Break, psi (MPa)	D1414	2150 (14.8)

\* Note: Unless otherwise indicated, all tests are performed on (-214) O-rings.

Statements and recommendations in this publication are based on our experience and knowledge of typical applications of this product and shall not constitute a guarantee of performance nor modify or alter of our standard warranty that shall be applicable to such products.

www.gtweed.com